



Accura[®] Amethyst

Specialty Class

High-resolution material for accurate master patterns for jewelry manufacturing

Post-Cured Material

MEASUREMENT	CONDITION	METRIC	U.S.
Tensile Strength (MPa/PSI)	ASTM D 638	22-38	
Tensile Modulus (MPa/KSI)	ASTM D 638	3514-3996	260-287
Elongation at Break (%)	ASTM D 638	0.56 - 1.04 %	0.56 - 1.04 %
Flexural Strength (MPa/PSI)	ASTM D 790	87-125	7540-10300
Flexural Modulus (MPa/KSI)	ASTM D 790	3652-3721	220-300
Impact Strength (J/m /Ft-lbs/in)	ASTM D 256	9-12	0.66-0.98
Heat Deflection Temperature	ASTM D 648 @ 66 PSI @ 264 PSI	77 °C 62 °C	170.6 °F 143.6 °F
Coefficient of Thermal Expansion (µm/m-°C / µm/in-°F)	ASTM E 831-93 TMA (T<Tg, 0-20 °C) TMA (T<Tg, 90-150 °C)	57 µ mm/m °C 133 µ mm/m °C	
Glass Transition (Tg)	DMA, E''	103 °C	217.4 °F
Hardness, Shore D		87	87

Liquid Material

MEASUREMENT	CONDITION	VALUE
Viscosity	@ 30 °C (86 °F)	350 cps
Penetration Depth (Dp)		3.7 mils
Critical Exposure (Ec)		14.4 mJ/cm ²
Color		Purple
Solid Density	@ 25 °C (77 °F)	1.23 g/cm ³ at 25 °C
Liquid Density	@ 25 °C (77 °F)	1.1 g/cm ³ at 25 °C
Tested Build Styles		EXACT [™] , FAST [™] , Exact HR [™]

Features

- Accurate, high-resolution master patterns
- High resolution in X, Y, and Z dimensions
- Manufacture master patterns for jewelry and other microcasting applications



www.3dsystems.com

UK
Tel: +44 1442 282 600
info@3dsystems-europe.com

**Germany, Scandinavia,
Eastern Europe, Middle East**
Tel: +49 6151 357 0
info@3dsystems-europe.com

USA
Tel: +1 803.326.3900
moreinfo@3dsystems.com

Asia-Pacific
Melbourne Tel: +61 3 9819 4422
Sydney Tel: +61 2 9516 5571
3dprinters.asiapac@3dsystems.com

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2017 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. The 3D logo and Accura are registered trademarks of 3D Systems, Inc.